

### **3M**

## Premium High Temperature Masking Tape

2393

**FOD# 1581** page 1 of 3

Technical Data			January 1, 1999	
		Supero	cedes September 1, 1998	
<b>Product Description</b>	A smooth, heavy duty, mini-crepe high temperature masking tape. It is specifically designed for those applications where easy removal after bake is important.			
<b>Product Construction</b>	Backing: A smooth mini-crepe paper treated with a heat resistant saturant Adhesive: A very high temperature heat resistant, smooth coated, rubber adhesive Color: Tan Standard Roll Length: 60 yds. (55m)			
Typical Physical Properties		nical information and data should be control to the used for specification purposes.	onsidered representative or	
		_	ASTM TEST METHOD	
	Adhesion to Steel:	33 oz./in. width (36 N/100mm)	D-3330	
	Tensile Strength:	28 lbs./in. width (490 N/100mm)	D-3759	
	Elongation at Break:	11%	D-3759	
	Tape Thickness:	7.6 mils (0.185mm)	D-3652	
	Temperature Use Range:	Up to 325°F (163°C) for 30 minutes		
General Information	Tape 2393 offers excellent paint mask performance with high solids paints and clear coats used in the transportation industry.			
	2. The special adhesive offers excellent adhesion to and easy removability from both metal and plastic.			
	3. Tape can be removed hot, warm or cold from most surfaces without adhesive transfer.			
	4. The heat resistance of this construction makes it suitable for bake cycles up to 325°F (163°C) for 30 minutes.			
	5. The smoothness of t	5. The smoothness of the backing makes this tape very "user friendly."		

# Scotch® Premium High Temperature Masking Tape 2393

page 2 of 3

FOD# 1581

### **General Information** (cont.)

- 6. Tape 2393 has excellent paint flake resistance.
- 7. The balanced construction with a stronger backing gives this tape easy removal properties without slivering.
- 8. Low unwind reduces workers' fatigue.
- 9. Can be left on job for an extended period of time and still remove cleanly.
- 10. Backing strength allows tape to be removed pulling through modern tough paints.
- 11. Tape 2393 should not be subjected to outdoor exposure or prolonged exposure to sunlight. Tape may become very difficult to remove.

#### **Shelf Life**

To obtain best performance, use this product within one year from date of manufacture and store under normal conditions of 70°F (21°C) and 50% R.H. in the original carton.

Features	FEATURES	ADVANTAGES	BENEFITS
	Rubber adhesive	Instant adhesion	Sticks easily/allows fast application
		Excellent holding power	Resists lifting or curling/ helps minimize rework
		Superior adhesive transfer resistance	Clean removal/helps minimize labor required to remove transferred adhesive
		Excellent high temperature performance	Holds firmly under heat strain yet removes cleanly
	Mini-crepe paper backing	Smoothness	Excellent surface contact/ secure holding/user friendly
		Thinness	Sharp paint line/quality paint job
		Dead stretch	Minimal recovery/helps reduce rework
		Conformability	Easy handling/allows fast application
	Backing saturant	Solvent and moisture resistance	Minimizes bleed-through and rework
		Easy tear	Excellent handling/helps reduce waste
	Special backsize treatment	Controlled unwind	Easy to use/helps reduce waste
		Good paint flaking resistance	Minimizes rework/clean paint shop environment

### Scotch® Premium High Temperature Masking Tape

**1 ape** FOD# 1581

2393 page 3 of 3

### **Technical Information** and **Data**

The technical information and data, recommendations, and other statements provided are based on tests or experience which 3M believes to be reliable, but the accuracy or completeness of such information is not guaranteed.

#### **Product Use**

Please remember that many factors can affect the use and performance of a 3M product in a particular application. The materials to be bonded with the product, the surface preparation of those materials, the product selected for use, the conditions in which the product is used, and the time and environmental conditions in which the product is expected to perform are among the many factors that can affect the use and performance of a 3M product. Given the variety of factors that can affect the use and performance of a 3M product, some of which are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method of application.

### Warranty and Limited Remedy

The 3M product will be free from defects in material and manufacture for a period of one (1) year from the date of manufacture. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's method of application. If the 3M product is defective within the warranty period stated above, your exclusive remedy and 3M's sole obligation shall be, at 3M's option, to replace or repair the 3M product or refund the purchase price of the 3M product.

#### **Limitation of Liability**

Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including contract, warranty, negligence, or strict liability.



#### **Industrial Tape and Specialties Division**

3M Center, Building 220-7W-03 St. Paul, MN 55144-1000 USA 1 800.722.5463 1 800.223.7427 Fax On Demand www.3M.com